

**TECHNICAL SPECIFICATIONS**

|                       |   |
|-----------------------|---|
| <b>Trade Name</b>     | Disks for Buchner funnels   |
| <b>Use</b>            | Useful interface between filter paper and perforated Buchner plate.<br>Avoids clogging of filters holes |
| <b>Material</b>       | Polyethylene PE   |
| <b>Other Features</b> | Texture 300 micron ( $\mu\text{m}$ )  |

**DIMENSIONAL SPECIFICATIONS**

|                    |     |
|--------------------|-----|
| <b>Diam. mm.</b>   | 110 |
| <b>For article</b> | 442 |

**GENERAL FEATURES**

|                |    |
|----------------|----|
| <b>CE Mark</b> | No |
|----------------|----|

**STERILIZATION**

|                                |     |
|--------------------------------|-----|
| <b>Autoclavability + 121°C</b> | No  |
| <b>Gas (Ethylene Oxide)</b>    | Yes |
| <b>Dry Heat (+160°C)</b>       | No  |
| <b>Chemical (Formalin)</b>     | Yes |
| <b>Irradiation</b>             | Yes |
| <b>Microwave</b>               | Yes |

**CLEANING OPERATIONS**

|                                 |   |
|---------------------------------|---|
| <b>Slight contamination</b>     | Wash with neutral detergent (pH 7)        |
| <b>Consistent contamination</b> | Wash with alkalin detergent (pH up to 12) |

**Quality Assurance**  
Massimiliano Capitanio

**CHEMICAL RESISTANCES**

| Categories of substances  | Reference         | Concentrazione % | T. 20° C | T. 40° C | T. 60° C |
|---------------------------|-------------------|------------------|----------|----------|----------|
| Inorganic Acid            | Sulphuric acid    | 98               | B        | B        | B        |
| Organic Acid              | Benzoic acid      | 100              | A        | A        | A        |
| Alcohol                   | Ethanol           | 100              | A        | A        | A        |
| Aldehydes                 | Acetaldeyde       | 100              | A        | B        | B        |
| Inorganic alkali          | Isodium hydroxide | 50               | A        | A        | A        |
| Organic alkali            | Aniline           | 100              | A        | B        | C        |
| Ketone                    | Acetone           | 100              |          |          |          |
| Esther                    | Ethyl acetate     | 100              | B        | B        | B        |
| Hydrocarbons, halogenated | Dichloroethylene  | 100              | B        | C        |          |
| Hydrocarbons, aromatic    | Benzene           | 100              | B        | B        | B        |
| Hydrocarbons, linear      | Hexane            | 100              | B        | B        | C        |
| Supersolvent              | Tetrahydrofuran   | 100              | B        | B        | B        |

**Legenda** (not applicable if neglected):

- **A: fair resistance**; exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance**; exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance**; exposure to chemical is not allowed, or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, steriization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products

**PACKAGING**

|     |        |
|-----|--------|
| Bag | 10 pcs |
|-----|--------|

**Quality Assurance**  
Massimiliano Capitanio