

TECHNICAL DATA SHEET ITEM 306

Mod. AQ 001 Rev. 0 del 25/09/2003

TECHNICAL SPECIFICATIONS

Trade Name Centrifuge tubes, cylindrical			
Use	Centrifuge tubes. Can also be used as conventional test tubes		
Material	PP		
Other Features	Rimmed. High chemical resistance		

DIMENSIONAL SPECIFICATIONS

Capacity	48 ml
Diameter	30 mm
Heigth	104 mm
RPM	4000
RCF X G	3000



GENERAL FEATURES

CE Mark	Yes
Foodstuff suitability	Yes

Temperature Resistance	Up to 120° C
Naked flame	CANNOT be used with nacked flame
Translucency	Very good

STERILIZATION

Autoclavability + 121°C	Yes
Gas (Ethylene Oxide)	Yes
Dry Heat (+160°C)	No
Chemical (Formalin)	Yes
Irradiation by Gamma	Yes
Microwave	Yes

CLEANING OPERATIONS

Slight contamination	Wash with neutral detergent (pH 7)
Consistent contamination	Wash with alkalin detergent (pH up to 12)

Quality Assurance

Technical Direction Guido Borona

Massimiliano Capitanio



TECHNICAL DATA SHEET ITEM 306

Mod. AQ 001 Rev. 0 del 25/09/2003

CHEMICAL RESISTANCES

Categories of substances	Reference	Concentrazione %	T. 20° C	T. 40° C	T. 60° C
Inorganic Acid	Sulphuric acid	98	В	С	-
Organic Acid	Benzoic acid	100	Α	В	В
Alcohol	Ethanol	100	Α	Α	Α
Aldehydes	Acetaldeyde	100	В	С	-
Inorganic alkali	Isodium hydroxide	50	Α	А	А
Organic alkali	Aniline	100	Α	В	O
Ketone	Acetone	100	-	-	-
Esther	Ethyl acetate	100	В	В	С
Hydrocarbons, halogenated	Dichloroethylene	100	С	-	-
Hydrocarbons, aromatic	Benzene	100	В	C	-
Hydrocarbons, linear	Hexane	100	В	В	С
Supersolvent	Tetrahydrofuran	100	В	В	С

Legenda (not applicable if neglected):

- A: fair resistence; exposure (30 days) to the chemical does not cause any damage.
- B: sufficient resistence; exposure causes damage of poor importance, which sometimes is only temporary.
- C: poor resistence; exposure to chemical is not allowed, or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, steriization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products

PACKAGING

Box		25 pcs

Quality Assurance Massimiliano Capitanio **Technical Direction**Guido Borona

