

TECHNICAL SPECIFICATIONS

Trade name	Graduated wide neck bottles
Use	Graduated bottle for liquids and powders; Sloping shoulders reduce tendency for residue deposits.
Material	Body in Polyethylene (PE); cap in Polypropylene (PP) and under cap in Polyethylene (LDPE)
Other features	Shoulder and cap with holes for safety seal or identification labels application. Permanent graduation printed in relief externally.

DIMENSIONAL SPECIFICATIONS

Height with mounted cap	158,00 mm
External base diameter	75,00 mm
Internal mouth diameter	34,50 mm
General dimensional tolerance	+/- 0,50 mm
Bottle wall thickness	1,00 +/- 0,20 mm
Capacity	500 ml
Graduated scale	50 ml each



GENERAL FEATURES

CE Mark	No
Foodstuff suitability	Yes, according to: EC Regulation 10/2011 The Italian Ministerial Decree 21/03/1973 and subsequent amendments The Italian Presidential Decree 777/82 and subsequent updates
Seal granted by	Quality of both cap and mouth thread, presence of the under cap
Translucent	Yes
Temperature range of the bottle	From -50°C to +80°C

BOTTLE STERILIZATION

Autoclavability +121°C	No
Gas (Ethylene Oxide)	Yes, without cap and undercap
Dry Heat (+160°C)	No
Chemical (Formalin)	Yes
Irradiation	Yes
Microwave	Yes, without cap and undercap

CLEANING OPERATIONS

Quality Assurance

Slight contamination	Wash with neutral detergent (pH 7)
Consistent contamination	Wash with alkaline detergent (pH up to 12)

CHEMICAL RESISTANCES (BOTTLE)

Categories of substances	Reference	Concen. %	T. 20° C	T. 40° C	T. 60° C
Inorganic acid	Sulphuric acid	98	B	B	B
Organic acid	Benzoic acid	100	A	A	A
Alcohol	Ethanol	100	A	B	B
Aldehydes	Acetaldehyde	100	B	C	-
Inorganic alkali	Sodium hydroxide	50	C	-	-
Organic alkali	Aniline	100	A	B	C
Ketone	Acetone	100	B	C	-
Esther	Ethyl acetate	100	B	C	-
Hydrocarbons, halogenated	Dichloroethylene	100	C	-	-
Hydrocarbons, aromatic	Benzene	100	B	C	-
Hydrocarbons, linear	Hexane	100	C	-	-
Supersolvent	Tetrahydrofuran	100	B	B	C

Legenda (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, sterilization and washing treatments are based on bulletins issued by the Producers of raw materials, on literature data and on the experience gained in using the products

PACKAGING

Quantity in each bag	20 pcs with mounted cap and undercap
Quantity for each box	8 x 20 = 160 pcs with mounted cap and undercap

Quality Assurance