

TECHNICAL DATA SHEET ITEM 1057

TECHNICAL SPECIFICATIONS

| Trade name | Industrial scoop |
|------------|------------------|
| Use | General use |
| Material | Polypropylene PP |

DIMENSIONAL SPECIFICATIONS

| Capacity | ml. 10 | |
|------------|-------------------|--|
| Dimensions | mm. 32 x 103 x 16 | |



GENERAL FEATURES

| CE mark | No |
|-----------------------|-----|
| Food contact suitable | Yes |

STERILIZATION

| Autoclavability + 121°C | Yes |
|-------------------------|-----|
| Gas (Ethylene Oxide) | Yes |
| Dry Heat (+160°C) | No |
| Chemical (Formalin) | Yes |
| Irradiation | Yes |
| Microwave | Yes |

CLEANING OPERATIONS

| Slight contamination | Wash with neutral detergent (pH 7) | |
|--------------------------|---|--|
| Consistent contamination | Wash with alkalin detergent (pH up to 12) | |

Quality Assurance

Technical Direction

Massimiliano Capitanio

Guido Borona

CHEMICAL RESISTANCE

| Reference | Concen. % | T. 20° | T. 40° | T.° 60 |
|------------------|---|--|---|--|
| Sulphuric acid | 98 | В | С | - |
| Benzoic acid | 100 | А | В | В |
| Ethanol | 100 | А | А | A |
| Acetaldehyde | 100 | В | С | - |
| Sodium hydroxide | 50 | А | Α | А |
| Aniline | 100 | А | В | С |
| Acetone | 100 | - | - | - |
| Ethyl acetate | 100 | В | В | С |
| Dichloroethylene | 100 | С | - | - |
| Benzene | 100 | В | С | - |
| Hexane | 100 | В | В | С |
| Tetrahydrofuran | 100 | В | В | С |
| | Sulphuric acid Benzoic acid Ethanol Acetaldehyde Sodium hydroxide Aniline Acetone Ethyl acetate Dichloroethylene Benzene Hexane | Sulphuric acid98Benzoic acid100Ethanol100Acetaldehyde100Sodium hydroxide50Aniline100Acetone100Ethyl acetate100Dichloroethylene100Benzene100Hexane100 | Sulphuric acid98BBenzoic acid100AEthanol100AAcetaldehyde100BSodium hydroxide50AAniline100AAcetone100-Ethyl acetate100BDichloroethylene100CBenzene100BHexane100B | Sulphuric acid98BCBenzoic acid100ABEthanol100AAAcetaldehyde100BCSodium hydroxide50AAAniline100ABAcetone100Ethyl acetate100BBDichloroethylene100C-Benzene100BCHexane100BB |

Legenda (not applicable if neglected):

A: fair resistence; exposure (30 days) to the chemical does not cause any damage.

- **B: sufficient resistence;** exposure causes damage of poor importance, which sometimes is only temporary.

C: poor resistence; exposure to chemical is not allowed, or causes immediate permanent damage.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

PACKAGING

Box

Pcs 12

Quality Assurance

Technical Direction

Massimiliano Capitanio

Guido Borona