

**TECHNICAL SPECIFICATIONS**

<b>Trade name</b>	Industrial scoop
<b>Use</b>	General use
<b>Material</b>	Polypropylene PP

**DIMENSIONAL SPECIFICATIONS**

<b>Capacity</b>	ml. 100
<b>Dimensions</b>	mm. 67,2 x 201,7 x 34

**GENERAL FEATURES**

<b>CE mark</b>	No
<b>Food contact suitable</b>	Yes

**STERILIZATION**

<b>Autoclavability + 121°C</b>	Yes
<b>Gas (Ethylene Oxide)</b>	Yes
<b>Dry Heat (+160°C)</b>	No
<b>Chemical (Formalin)</b>	Yes
<b>Irradiation</b>	Yes
<b>Microwave</b>	Yes

**CLEANING OPERATIONS**

<b>Slight contamination</b>	Wash with neutral detergent (pH 7)
<b>Consistent contamination</b>	Wash with alkalin detergent (pH up to 12)

**Quality Assurance**

Massimiliano Capitanio

**Technical Direction**

Guido Borona

**CHEMICAL RESISTANCE**

Categories of substances	Reference	Concen. %	T. 20°	T. 40°	T.° 60
Inorganic acid	Sulphuric acid	98	B	C	-
Organic acid	Benzoic acid	100	A	B	B
Alcohol	Ethanol	100	A	A	A
Aldehydes	Acetaldehyde	100	B	C	-
Inorganic alkali	Sodium hydroxide	50	A	A	A
Organic alkali	Aniline	100	A	B	C
Ketone	Acetone	100	-	-	-
Esther	Ethyl acetate	100	B	B	C
Hydrocarbons, halogenated	Dichloroethylene	100	C	-	-
Hydrocarbons, aromatic	Benzene	100	B	C	-
Hydrocarbons, linear	Hexane	100	B	B	C
Supersolvent	Tetrahydrofuran	100	B	B	C

**Legenda** (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damage.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing..

**PACKAGING**

Box	Pcs 12
-----	--------

**Quality Assurance**

Massimiliano Capitanio

**Technical Direction**

Guido Borona