

TECHNICAL SPECIFICATIONS

Trade Name	Graduated tall form measuring cylinders -
Use	Volumetric measures
Material	Polypropylene PP
Other Features	Permanent graduations are moulded in for reproducibility

DIMENSIONAL SPECIFICATIONS

Height	315,00 mm
External diameter	41,50 mm
General dimensional tolerance	ISO 6706
Capacity	250 ml
Graduated	20 ml each
Graduation Class	B

**GENERAL FEATURES**

CE Mark	No
Foodstuff suitability of the raw material	Yes
No wetting	Yes
Chemically cleaner than glass	Yes
Chemically non absorbant	Yes
Manufactured in compliance with	ISO 6706 -1981
Aspect	Translucent

STERILIZATION

Autoclavability + 121°C	Yes
Gas (Ethylene Oxide)	Yes
Dry Heat (+160°C)	No
Chemical (Formalin)	Yes
Irradiation	Yes
Microwave	Yes

CLEANING OPERATIONS

Slight contamination	Wash with neutral detergent (pH 7)
Consistent contamination	Wash with alkaline detergent (pH up to 12)

Quality Assurance

CHEMICAL RESISTANCES (Polypropylene)

Categories of substances	Reference	Concentrazione %	T. 20° C	T. 40° C	T. 60° C
Inorganic Acid	Sulphuric acid	98	B	C	-
Organic Acid	Benzoic acid	100	A	B	B
Alcohol	Ethanol	100	A	A	A
Aldehydes	Acetaldeyde	100	B	C	-
Inorganic alkali	Isodium hydroxide	50	A	A	A
Organic alkali	Aniline	100	A	B	C
Ketone	Acetone	100	-	-	-
Esther	Ethyl acetate	100	B	B	C
Hydrocarbons, halogenated	Dichloroethylene	100	C	-	-
Hydrocarbons, aromatic	Benzene	100	B	C	-
Hydrocarbons, linear	Hexane	100	B	B	C
Supersolvent	Tetrahydrofuran	100	B	B	C

Legenda (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, sterilisation and washing treatments are based on bulletins issued by the Producers of raw materials, on literature data and on the experience gained in using the products

PACKAGING

Minimum pack	12 pcs
Case	108 pcs

Quality Assurance